

TECHNICAL SHEET	CEMENT ADHESIVE	 EN 12004-1:2017	Designation according to the standard <b>C1T</b>
-----------------	-----------------	--	---

Revision: 01.01-28/01/25

# Adimar Gypsum

The **Adimar Gypsum** adhesive for ceramic tiles manufactured by AYMAR S.A.U. is a cementitious adhesive with reduced slip type C1T in accordance with the EN 12004:2017 standard, designed with marble aggregates, cement and special additives that give it adhesion, sliding and water retention properties ideal for the installation of ceramic pieces.

## Composition

Composed of crushed marble aggregates used in construction, Portland cement and both organic and inorganic additives that give it better characteristics in adhesion and sliding.

## Field of application

Adimar Plaster has special characteristics for the installation of tiles, stoneware of medium/high porosity, in interior cladding, on traditional plaster plaster supports, boards and prefabricated gypsum panels, suitable for anhydrite supports. Not suitable for outdoor use.

## Instructions for use

- **Preparation of the support:** the support on which the application is to be carried out must be resistant, dry, level, clean of dust and free of traces of release agent.
- **Preparation of the mixture:** add 6-6.5 l of water per bag and mix manually or mechanically, with a low-speed electric whisk, to eliminate any possible lumps in the pasta, let the mixture rest for 5 minutes and make a brief kneading.
- **Application of the paste:** apply the product on the substrate using a toothed trowel, to regularize the thickness, in a maximum area of 2 m<sup>2</sup>, applying enough pressure so that the minimum contact with the cement is 80%. Place the tiles by pressing them until the grooves are flattened and the piece is properly solidized with the help of a rubber mallet. It is necessary to check, with your fingertips, periodically that the adhesive has not formed a film on its surface, if this happens, the product must be combed again, taking into account that we are still in the margin of the open time of the product (if the time period since its application has exceeded the aforementioned open time, the adhesive must be removed and reapplied).

## Recommendations for use

- The application temperature must be between 5 °C and 35 °C on the support.
- Do not apply outdoors.
- Evitar Avoid laying on weak plaster. If necessary, apply a hardening surface treatment by means of a primer.
- Do not apply on substrates with residual humidity > 5%.
- Check the planimetry of the support with a 2 m ruler, verifying that the deviations must be less than 5 mm. In the event of higher deviations, they must be regularized before installation.

## Recommendations for use

- Do not use in areas where there is a danger of standing water.
- It is advisable to leave a minimum of 2mm joint between tiles by applying **JOINT UNIVERSAL 0/15** or **TECHNICAL JOINT 0/16**.
- On very absorbent substrates, it is advisable to moisten it and wait until it is dry.
- Check the solidity of the finishing plaster of the precast plaster.
- To install low-absorption porcelain stoneware ceramics on a plaster support, use **Adimar Porcelain** or **Adimar Flexible**.

## Technical Data

Product	Type	C1T		Classification according to the standard EN 12004-1:2017
	Color	White/Grey		
Application	Kneading water	25%		
	Maturation Time	5'		
	Open Time	20'	EN 12004-2:2017	
	Slide	< 0,5 mm	EN 12004-2:2017	
	Grouting at the	24h		
	Walkable to	24h (Light traffic)		
Final yields	Initial adhesion	>0,5N/mm <sup>2</sup>	EN 12004-2:2017	
	Adhesion after immersion in water	>0,5 N/mm <sup>2</sup>		
	Open Time Adhesion, 20'	>0,5 N/mm <sup>2</sup>		
Storage	12 months	Store with the container closed and in a covered, dry and ventilated place		
Presentation	25 kg bags			
HS Code	38245090			

## MADE IN SPAIN

For safety precautions in the use, storage and disposal of the product, please refer to the Safety Data Sheet available on the website [www.aymarsa.es](http://www.aymarsa.es)

**NOTE:** The information contained in this technical sheet is based on our experience and tests carried out in specialized laboratories. The characteristics of the resulting product will depend on the correct preparation and application on site by the user. If these conditions are not met, the characteristics indicated above will not be achieved.



### Plant & Offices

Ctra. C-35, Km 58 · Ap. correos nº1  
08470 SANT CELONI (Barcelona)

Tel. (+34) 93 867 00 00

aymar@aymarsa.es  
[www.aymarsa.es](http://www.aymarsa.es)




SGM-001/2009



ER-1277/2010



SST-006/2018



GA-2010/0955  
Mina "XAUXA"



Gestión ambiental verificada  
REG. Nº. ES-CAT-10001  
Mina "Xausa"